CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

An ISO 9001:2008 Certified Company

Job No.: CTCE/BBMP/W.No.06/HSN/WMM/Gradation/2013-14 18.12.2013

GRADATION FOR WMM

MORTH TABLE-400-11

Client : **Asst. Executive Engineer,** Byatarayanapura Sub Division, BBMP, Bangalore.

Agency : **Mr. H.S. Nataraj,** Contractor,Bangalore.

Name of Work : Providing and asphalting to road at Bhuvaneshwarinagara in Ward No.06 Byatarayanapura Sub Division, BBMP, Bangalore.

Reference : EE/BTP/BBMP/E-TND/444/2012-13 Dated: 16.03.2013

Date of Testing : 18.12.2013

Material : WMM

Sample Location : WMM Mix Plant Oven Dry Wt (gm): **8365**

Is Sieve Size in mm	Weight Retained (gm)	Cumulative Weight Retained (gm)	Cumulative % of Retained	Cumulative % of Passing	Spec.Limits
53	0	0	0	100	100
45	255	255	3.0	97.0	95-100
22.4	2850	3105	37.1	62.9	60-80
11.2	1610	4715	56.4	43.6	40-60
4.75	1025	5740	68.6	31.4	25-40
2.36	955	6695	80.0	20.0	15-30
0.600	895	7590	90.7	9.3	8-22
0.075	525	8115	97.0	3.0	0-8

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

M/s. Civil-Tech Consultants & Engineers
23/14, 7th Cross, 3rd Stage,
4th Block, Shakthiganapathinagara,
Basaveshwaranagar,
Bangalore-560079.

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

An ISO 9001:2008 Certified Company

JAS-ANZ BSCIC ISO 9001 REGISTERED

Job No.: CTCE/BBMP/W.No.06/HSN/SDBC/Bitumen/2013-14 · 24.12.2013

BITUMEN CONTENT AND GRADATION DETERMINATION OF SEMI DENSE BITUMINOUS CONCRETE MIX
As per IS2386 and IRC:SP:11-1984

CLIENT	**Asst. Executive Engineer,** Byatarayanapura Sub Division, BBMP, Bangalore.
AGENCY	**Mr. H.S. Nataraj,** Contractor,Bangalore.
NAME OF THE WORK	Providing and asphalting to road at Bhuvaneshwarinagara in Ward No.06 Byatarayanapura Sub Division, BBMP, Bangalore.
REFERENCE	EE/BTP/BBMP/E-TND/444/2012-13 Dated: 16.03.2013
SAMPLE I/D	Roads in Bhuvaneshwarinagara in Ward No.06, BBMP, Bangalore.
DATE OF TESTING	24.12.2013

BITUMEN CONTENT DETERMINATION

Description	Trail 1	Trail 2
1. Weight of Mixture before Test, g	500	500
2. Weight of Mixture after Test, g	475	474.5
3. Weight of Asphalt and Mineral matter Extracted,	-	-
4. Weight of Mineral Matter, g.	-	-
5. Weight of Ash, g		
6. Weight of Bitumen Extracted, g. (corrected)	25	25.50
7. Bitumen content in %	5.00	5.10
8. Average	**5.05**	

GRADATION AFTER EXTRACTION

SIEVE SIZE	Trail 1				JOBMIX
mm	Weight Retained, gm	% Retained	%Cummulative Retained	% Passing	Gradation
13.2	0	0	0	100	100
9.5	33.32	7.01	7.01	92.99	90-100
4.75	260.5	54.84	61.86	38.14	35-51
2.36	45.25	9.53	71.38	28.62	24-39
1.18	36.36	7.65	79.04	20.96	15-30
0.3	40.22	8.47	87.51	12.49	9-19
0.075	36.36	7.65	95.16	4.84	3-8

SIEVE SIZE	Trail 2				JOBMIX
mm	Weight Retained, gm	% Retained	%Cummulative Retained	% Passing	Gradation
13.2	0	0	0	100	100
9.5	35.23	7.05	7.05	92.95	90-100
4.75	256.3	51.26	58.31	41.69	35-51
2.36	32.25	6.45	64.76	35.24	24-39
1.18	46.35	9.27	74.03	25.97	15-30
0.3	49.36	9.87	83.90	16.10	9-19
0.075	52.32	10.46	94.36	5.64	3-8

Note:

- This test report should not be reproduced except in full, without written approval of the laboratory
- The results indicated above are based on the tests carried out on the samples received in the laboratory
- Any Query regarding the report must be reported within 30 days from the date of testing.

M/s. Civil-Tech Consultants & Engineers

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagara, Bangalore-79.
Tele fax : 23223227, Cell : 93428 39190, Website : www.civiltechconsultants.com
e-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com

Civil-Tech Consultants & Engineers Bangalore

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagara, Bangalore-560079.